

## Moplen HP500N

### Polypropylene, Homopolymer

#### Product Description

Moplen HP500N is a homopolymer used for general purpose injection moulding applications. It exhibits good flow and stiffness.

Moplen HP500N is suitable for food contact.

#### Product Characteristics

<b>Status</b>	Commercial: Active
<b>Test Method used</b>	ISO
<b>Availability</b>	Europe, Africa-Middle East

Typical Properties	Method	Value	Unit
<b>Physical</b>			
Density	ISO 1183	0.9	g/cm <sup>3</sup>
Melt flow rate (MFR) (230°C/2.16kg)	ISO 1133	12	g/10 min
Melt volume flow rate (230°C/2.16kg)	ISO 1133	16	cm <sup>3</sup> /10min
<b>Mechanical</b>			
Tensile Modulus	ISO 527-1, -2	1550	MPa
Tensile Stress at Yield	ISO 527-1, -2	35	MPa
Tensile Strain at Break	ISO 527-1, -2	>50	%
Tensile Strain at Yield	ISO 527-1, -2	10	%
<b>Impact</b>			
Charpy unnotched impact strength (23 °C, Type 1, Edgewise)	ISO 179	110	kJ/m <sup>2</sup>
(0 °C, Type 1, Edgewise)		30	kJ/m <sup>2</sup>
Charpy notched impact strength (23 °C, Type 1, Edgewise, Notch A)	ISO 179	3	kJ/m <sup>2</sup>
<b>Thermal</b>			
Heat deflection temperature B (0.45 MPa) Unannealed	ISO 75B-1, -2	95	°C
Vicat softening temperature A/50	ISO 306	153	°C
Vicat softening temperature B/50	ISO 306	85	°C

#### Notes

Typical properties; not to be construed as specifications.

Copyright 2009 Basell Service Company B.V. All rights reserved.

For the contact details of the LyondellBasell company selling this product in your country, please visit <http://www.lyondellbasell.com/>.

Before using a LyondellBasell product, customers and other users should make their own independent determination that the product is suitable for the intended use. They should also ensure that they can use the LyondellBasell product safely and legally. This document does not constitute a warranty, express or