

**Product Description**

EL-LENE™ D795C is an Autoclave LDPE grade for extrusion coating/lamination.

Typical Application

- General extrusion coating, extrusion lamination, co-extrusion coating
- For coating on different substrates; Aluminium foil, paper, tarpaulin and flexible films(PET, OPP, Nylon,..)
- Food and non-food packaging

Product Characteristics

- Low neck-in
- Good processibility
- Good thickness control and edge stability

International Standard Compliance

- U.S FDA 21 CFR 177.1520
- Regulation (EU) No.10/2011
- Regulation (EC) 2023/2006 (GMP)
- Packaging and Packaging waste Directive 94/62/EC

Note: Direct food contact is subjected to the extraction provisions of the regulation on the finished food contact package

Physical properties

Properties	Test Method	Typical Value	Unit
Resin Properties			
Melt Flow Rate	ASTM D 1238 @ 190 °C, 2.16 kg	9.0	g/10 min
Density	ASTM D 1505	0.918	g/cm ³
Melting Point	ASTM D 2117	107	°C
Vicat Softening Point	ASTM D 1525	85	°C
Coating Properties			
Neck-in (315 °C) (Constant output at 50 rpm)	TPE Method	6	cm

Processing Guidelines

For extrusion coating of D795C, it is recommended to apply primer or corona treatment on substrate before coating for better adhesion.

The actual extrusion condition depends on the type of machine, size and thickness.

Generally, melt temperature 300-330 °C. should be obtained. Minimum recommended air gap is 150 mm.

Product Technical Assistance

For technical assistance or further information on this product or any other SCG Chemicals' products, please contact your SCG Chemicals technical service at the address or telephone number as specified below.

Product Available Form

- Pellet

Product Packaging

- 25 kg loose bag
- Big bag with specified weight

SCG Plastics Company Limited / SCG Performance Chemicals Company Limited

1 Siam Cement Road, Bangsue, Bangkok, 10800 Thailand.

Tel. +66 2586 4874 Fax +66 2586 4140 www.chemicals.scg.co.th

PD-D-0023 Rev 000.

Rev. Aug' 13 Valid until next revision



Storage

- Store in original container in tidy according to the manual of Handling and Storage from Thai Polyethylene Company Limited.
- Product(s) should be stored in dry and dust free location at temperature below 50°C and protected from direct sunlight and/or heat, well-ventilated area, away from incompatible materials and food and drink, as this may lead to quality deterioration, which results in odour generation and colour changes and can have negative effects on the physical properties of this product.
- Keep container tightly closed and sealed until ready for use. Containers that have been opened must be carefully resealed and kept upright to prevent leakage. Do not store in unlabelled containers. Use appropriate containment to avoid environmental contamination.
- The storage area should be stable and not be slopped.

Safety

- The product is not classified as a hazardous material.
- Please see our Material Safety Data Sheet for details on various aspects of safety, recovery, and disposal of the products, for more information contact your SCG Chemicals technical service.
- This datasheet is valid for prime product specification only.
- For near and wide product specification, we do not recommend using in food contact application.

Recycling

- The product is suitable for recycling using modern methods of shredding and cleaning. In-house production waste should be kept clean to facilitate direct recycling.
- Please see our Material Safety Data Sheet for details on various aspects of safety, recovery and disposal of the product, for more information contact your SCG Chemicals technical service.

Related Documents

The following related documents are available on request, and represent various aspects on the usability, safety, recovery and disposal of the product.

- Material Safety Data Sheet
- Statement on compliance to food contact regulations

Disclaimer

- This product(s) can be used only for the application as specified hereabove.
- To the best of our knowledge, the information contained herein is accurate and reliable as of the date of publication, however we do not assume any liability whatsoever for the accuracy and completeness of such information.
- We make no warranties which extend beyond the description contained herein. Nothing herein shall constitute any warranty of merchantability or fitness for a particular purpose.
- It is the customer's responsibility to inspect and test our products in order to satisfy itself as to the suitability of the products for the customer's particular purpose. The customer is responsible for the appropriate, safe and legal use, processing and handling of our products.
- No liability can be accepted in respect of the use of our products in conjunction with other materials. The information contained herein relates exclusively to our products when not used in conjunction with any third party materials.

EL-Lene™ EL-Pro™ EL-Wax™ 

are registered trademarks of SCG Chemicals, Thailand.

SCG Plastics Company Limited / SCG Performance Chemicals Company Limited

1 Siam Cement Road, Bangsue, Bangkok, 10800 Thailand.

Tel. +66 2586 4874 Fax +66 2586 4140 www.chemicals.scg.co.th

PD-D-0023 Rev 000.

Rev. Aug' 13 Valid until next revision